


Environmental Impact Report

Bigagli PETT • Date of issue: 27-06-2023









Environmental savings of PETT compared to reference:







Calculation of impact per 1 kg	kg CO2 eq	Energy Usage in MJ	Water Consumption in Liters	Land Use m2 crop eq
Fibers	2,41	27,7	13,2	0,0
Fabric production	0,93	9,4	8,9	0,1
Finishing	3,60	42,0	146,5	0,0
Packaging	0,09	2,3	1,4	0,0
Transport	0,21	3,0	0,4	0,0
Total (per 1 kg)	7,24	84,3	170,3	0,2

The calculation of the bAwear-Score is based on the proprietary bAwear textile model and SimaPro software and on the input (primary data) provided. In case primary data was lacking, secondary data was used. The secondary data are extracted from the Ecolovent[®] database and publicly available literature sources. When using secondary data (in part or solely), the results of the calculation are only indicative. The calculations are performed using ReCiPe 2016 midpoint method. Data security is covered by our partner PRé Sustainability, having implemented ISO 27001:2013



Lanificio Bigagli PETT

Felt from recycled plastic bottles

Composition:

Polyester recycle	ed 96 %
Polyester	04 %
Production:	Italy
Data per:	1000 gram

Based on partially primary data supplied by Bigagli